
Ecophon Clipso™ So Acoustic Antibacterial

Ecophon ClipsoTM So Acoustic Antibacterial is a micro perforated knit fabric with a uniform coating, that can be combined with an acoustic absorbent to reduce noise levels. With its Sanitized® antimicrobial protection, Clipso So Acoustic Antibacterial is suitable for healthcare premises and other environments in need of antibacterial properties on ceiling and walls.




SYSTEM RANGE



Size, mm	×2000	×2500	x3000	×4000	x5100
Ceiling	•	•	•	•	•
Wall	•	•	•	•	•
Thickness (THK)	0,4	0,4	0,4	0,4	0,4
Inst. Diagr.	M596 , M597, M598				











Clipso technical fabric.


Acoustic



Sound Absorption:

Test results according to EN ISO 354. Classification according to EN ISO 11654.

 $\alpha_{_{D^{\prime}}}$ Practical sound absorption coefficient



- --- So Acoustic 495D AB GW20, 200 mm o.d.s.
- So Acoustic 495D AB GW40, 200 mm o.d.s.
- So Acoustic 495D AB LA10, 10mm o.d.s.
- ···· So Acoustic 495D AB LA50, 200mm o.d.s.
- --- So Acoustic 495D AB no absorber, 200mm o.d.s.

o.d.s = overall depth of system

	THK			α _p , Prac	ctical sound	dabsorption	coefficient		$\alpha_{\scriptscriptstyle \text{VV}}$	Sound absorption class
	mm	o.d.s. mm	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	$\alpha_{\rm w}$	Sound absorption class
495D AB GW20	20	200	0.20	0.65	0.90	0.75	0.90	0.90	0.85	В
495D AB GW40	40	200	0.30	0.85	0.95	0.85	0.95	0.95	0.95	А
495D AB LA10	10	10	0.10	0.25	0.45	0.65	0.95	1.00	0.50	D
495D AB LA50	50	200	0.30	0.90	0.85	0.75	0.85	0.85	0.85	В
495D AB	0	200	0.10	0.50	0.75	0.65	0.70	0.70	0.70	С

Frequency Hz

	THK mm	o.d.s. mm	NRC	SAA
495D AB LA10	10	10	0.60	0.57
495D AB LA50	50	200	0.85	0.83
495D AB	0	200	0.65	0.65

Indoor Air Quality



Certificate / Label	Clipso Technical Fabric	Clipso LA absorber	Ecophon acoustic board for Clipso
Eurofins Indoor Air Comfort®	IAC Gold	-	IAC Gold
French VOC	A+	A+	A+
Greenguard	Gold	-	-









Fire safety

Country	Fire standard	Class
Europe	EN 13501-1	B-s 1 ,d0



Humidity Resistance

Property	Standard/Method	Performance
Dimensional stability under the action of humidity	EN 14716 (appendix C)	0% (MD), 0% (CMD)
Dimensional stability under the action of heat	EN 12280-1 (30 min, 60°C)	0% (MD), 0% (CMD)
Water vapour transmission rate	ISO 2528 (38°C, 90% RH)	1084 g/m²

\$)))

Visual appearance

Matt, smooth and uniform. Nearest colour sample RAL 9016.



Cleanability

Use of Clipso Cleaning Kit recommended. Alternatively, other pH-neutral cleaning agents can be used with a soft cloth, provided it has first been tested on a scrap piece or on a non-visible area of the fabric.



Advanced Cleanability

Steam cleaning. Compatible with UV-C disinfection, BIFMA HCF 8.1-2019.



Surface Endurance

Product tested according to ISO 11998, and withstand 200 cycles.



Chemical resistance/Disinfection

Chemical	Active Substance	Concentration	
Ethanol	Ethanol	70%	
Virkon S	Dipotassium peroxodisulphate; Sulphamidic acid	1%	
Isopropanol	Isopropyl Alcohol	70%	
Anioxy- Spray	Hydrogen peroxide	5%	
Sumabac D10	Quaternary ammonium compound, Sodium carbonate	1%	

Tested according to ISO 11998 and withstand the following chemicals or disinfectants.



Mould and Bacterial Resistance

Standard/Method	
ISO 846 A	0
ISO 846 C	0
Sanitized®	Compliant



Sanitized® Hygiene Function and Material Protection is a treatment that eliminates harmful microorganisms and provides a barrier against contamination, ensuring cleanliness and safety in areas where it matters the most.

Accessibility



The system supports installation of inspection hatches.



Clean Room

	Class	
ISO 14644	Particle cleanliness class	ISO 4
NF S 90-351	Microbiological class	M1/area 4
NF S 90-351	Particle elimination kinetics	CP(0,5) 5



Installation

Installed with Clipso profiles according to installation diagrams and drawing aid. Non-magnetic system when specific fixation screws are used.



System weight

Area weight 230 g/m 2 ± 10% (ISO 2286-2)



Mechanical properties

Property	Standard/Method	Performance
Tensile strength	ISO 1421	30 daN/5 cm (MD), 54 daN/5 cm (CMD) (495D) 29 daN/5 cm (MD), 107 daN/5 cm (CMD) (495AC)
Tear strength	en 1875-3	8.9 daN (MD), 15.9 daN (CMD) (495D) 10.8 daN (MD), 17.7 daN (CMD) (495AC)

Additional load (lighting, ventilation, etc.) should be hung directly from the soffit.




CE

Clipso technical fabrics are CE-marked according to the European harmonized standard EN14716:2005. CE marked construction products are covered by a Declaration of Performance (DOP) which enables customers and users to easily compare performance of products available on the European market.


© Saint-Gobain Ecophon AB


Ecophon Clipso™ So Acoustic Antibacterial, 2024-




QUANTITY SPECIFICATION (EXCL. WASTAGE)

		Size, mm				
		×2000	×2500	×3000	x4000	x5100
1	Clipso 495 D AB technical fabric	as required	-	as required	as required	as required
2	Alt 1 - Acoustic absorbers for Clipso technical fabrics (glass wool)	as required		as required	as required	as required
	Alt 2 - Acoustic absorbers for Clipso technical fabrics (polyester fiber)	as required	-	as required	as required	as required
3	Clipso PCW profiles	as required				
	Installation and maintenance accessories for Clipso technical fabrics	-	-	-	-	-








QUANTITY SPECIFICATION (EXCL. WASTAGE)

	Size, mm							
	×2000	×2500	×3000	×4000	x5100			
Clipso 495 D AB technical fabric	as required	-	as required	as required	as required			
Wall absorbers for Clipso technical fabrics	as required							
Clipso PCC profiles	as required							
Installation and maintenance accessories for Clipso technical fabrics	-	-	-	-	-			



QUANTITY SPECIFICATION (EXCL. WASTAGE)

	Size, mm							
	×2000	×2500	×3000	×4000	x5100			
Clipso 495 D AB technical fabric	as required		as required	as required	as required			
2 Clipso PCC profiles	as required							
Installation and maintenance accessories for Clipso technical fabrics	-	-	-	-	-			